

## STYLE 500 COMPRESSED SHEET

**Color:** Gray/Black

Manufactured from 95% pure graphite with a .002" thick 316 stainless steel insert that reduces gasket handling damage and increases pressure resistance. Style 500 has no binders or resins to cook out and will not cold flow. Temperatures to -328° to 5432°F. Pressures up to 5000+ psi and a pH range of 0-14.

**Sizes:** 60" x 60"

**Thickness:** 1/64", 1/32", 1/16", 3/32", 1/8", 1/4".



## STYLE 6234 COMPRESSED SHEET/NITRILE BINDER

**Color:** Off White

Manufactured with a special compound of heat and chemical resistant nitrile rubber and non-asbestos fibers. This blend of organic fibers exhibits the highest chemical and temperature resistance of all the non-asbestos compressed sheet we offer. Temperatures to 750°F/400°C. Pressures to 1450 psi/100 bar.

Recommended for mating flanges in applications sealing steam, air, gases, ammonia, chemicals, and many acids and caustic solutions.

**Sizes:** 60" x 180"

**Thickness:** 1/64", 1/32", 1/16", 3/32", 1/8", 1/4".



## STYLE 6234C COMPRESSED SHEET/NITRILE BINDER

**Color:** Black

Manufactured with a special compound of heat and chemical resistant nitrile rubber and carbon fibers. This blend of carbon fibers exhibits the highest chemical and temperature resistance of all the non-asbestos compressed sheet we offer. Temperatures to 750°F/400°C. Recommended for mating flanges in applications sealing steam, air, gases, ammonia, chemicals, and many acids and caustic solutions.

**Sizes:** 60" x 180"

**Thickness:** 1/64", 1/32", 1/16", 3/32", 1/8", 1/4".



*"Since the performance of the gasket material is dependent on many other factors not related to the gasket itself, Purchaser is WARNED that the maximum operating conditions shown in the 'Technical Data' chart may not be achieved under certain conditions. Purchaser is therefore urged to test the gasket material under the actual conditions of assembly and operation to determine the appropriate maximum operating conditions."*